

Technical Data Sheet

Norox[®] MEKP-9H

DESCRIPTION

Norox[®] MEKP-9H features a reduced level of hydrogen peroxide. Norox[®] MEKP-9H is particularly useful in critical gel coat applications. Another area of application is in heated, continuous mixing systems for polymer concrete and cultured marble.

TYPICAL PROPERTIES

Active Oxygen:	9.0% max.
Form:	Liquid
Color:	Water white
Specific Gravity @ 25°/4°C:	1.11
Flash point (C.O.C.):	200°F, min.
Flash point (SETA C.C.):	170°F, min.
Soluble in:	Oxygenated organic solvents
Slightly soluble in:	Water

APPLICATION

Norox[®] MEKP-9H is an excellent liquid general-purpose cure initiator for the room temperature cure of polyester resins. In this application it imparts medium to high exotherm characteristics to the cure. Norox[®] MEKP-9H gives excellent performance as a curing agent for gel coats. Resin suppliers should be consulted for specific recommendations for individual resins. Norox[®] MEKP-9H is highly refined and substantially free of water, hydrogen peroxide and methyl ethyl ketone. Compared to Norox[®] MEKP-9, with most polyester resins Norox[®] MEKP-9H gives a slightly longer gel time with a similar total cure time.

PACKAGING, SHIPPING & AVAILABILITY

- The standard package sizes of Norox[®] MEKP-9H are cases of 4x8 lb. and 4x4 kg polyethylene bottles; and 40 lb. or 20 kg Hedpacks. For custom package sizes, please contact your local distributor or United Initiators SPI, Inc.
 - Classification – Please refer to the specific Norox[®] MEKP-9H Safety Data Sheet under section 14, Shipping Description.
 - Norox[®] MEKP-9H is available through a nation-wide distributor network. Call United Initiators SPI, Inc. for the name of the distributor in your area.
- **NOTE:** SDS's for all our products may be requested thru the website www.syrqispi.com

Disclaimer

This information and our application-technical advice – whether verbal, in writing or by way of trials – reflect our present state of knowledge based on internal tests with local raw materials. Their purpose is to inform interested parties about our products and their possible application. They should not be construed as guaranteeing specific product properties or their suitability for a particular application. Furthermore, the information does not contain complete instructions for use. Nor does it constitute a guarantee as to quality and durability. Changes due to technical progress and corporate advancement reserved. Any existing third-party copyrights are to be taken into account.

Application and use of our products based on our application-specific advice is beyond our control and sole responsibility of the user. The user is not released from the obligation of verifying the suitability and applicability as to the intended purpose.